

PRIMABAKE LIGHT

Specification sheet

Light release **paper process** with a delicate silicone treatment on both sides alongside greaseproof properties.

Typical end-use

An environmentally friendly paper ideal for industrial baking applications, light release, with excellent heat stability for single use applications.

INCREASING NUMBER OF BAKES

Varies upon baked goods, time, temperature and operators.



LIGHT

CLASSIC

STAR

Regulation and food contact approval

Meets regulatory international requirements on the food contact.

Cf. Declaration of compliance:

<https://primabake.com>

FSC® & PEFC on request.

Specifications					
Property	Test Method	Unit	Typical value		
Grammage	ISO 536	g/m ²	39		41
Shade		/	White	Unbleached*	White
Moisture	ISO 287	%	4.0	4.0	4.0
Thickness	ISO534	µm	48	48	50
ISO Brightness	ISO 2470-1	%	>76%	/	>76%
Bursting Strength after heating (200°C /20 mn)	ISO 2758	kPa	≥85	≥85	≥95
Water Absorbency Cobb 60	ISO 535	g/m ²	16	17	17
Oil Absorbency Cobb 60- Unger	SCAN -P 37-77	g/m ²	3.8	3.8	3.8
Sponge cake 8 min/225 °C	PDL method	g/m ²	≤45	≤45	≤45
Pretzel test	PDL method		Not OK	Not OK	Not OK

Paper tolerances	
Grammage : ± 1,5 g/m ²	Moisture : ± 1 %
Thickness : +3/ -2 µm	Oil Absorbency Cobb 60- Unger: max 7 g/m ²
Water Absorbency Cobb 60: max + 2 g/m ²	

Available in reel and sheet			
Reel		Sheet	
Min. reel diameter	On demand	Box	500 or 1000
Max. reel diameter	115 cm	Packet	500
Cores	70/76/120/152 mm		
Finished goods tolerance			
Width customer tolerance: (- 2mm,+ 0)		Size: (- 2mm, +0)	
Mill splice : Maxi 3 per reel with at least 60% of the reels without			
Outer diameter: (-2 cm, + 0). Length (0/+100 m)			

Measurements made according to the standards and norms in place at time of publication.

Please contact your sales representative for more details.

Validated: Hervé BRUNET-JAILLY

Date: 15th July 2021